

इंटरनेट

मानक

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan

“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”

IS 4843 (1968): Code for designation of ferrous castings
[MTD 14: Foundry]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”

BLANK PAGE



IS : 4843 - 1968

Indian Standard

CODE FOR DESIGNATION OF
FERROUS CASTINGS

(Second Reprint AUGUST 1982)

UDC 669.13-14:003.62



© Copyright 1969

INDIAN STANDARDS INSTITUTION
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

Price Rs 5-00

January 1969

Indian Standard

CODE FOR DESIGNATION OF FERROUS CASTINGS

Metal Standards Sectional Committee, SMDC 1

<i>Chairman</i>	<i>Representing</i>
SHRI R. G. BHATAWADEKAR	The Binani Metal Works Ltd, Calcutta
<i>Members</i>	
DR U. N. BHRANY	The Indian Iron & Steel Co Ltd, Burnpur
SHRI K. H. SHARMA (<i>Alternate</i>)	National Metallurgical Laboratory (CSIR), Jamshedpur
SHRI B. N. DAS	Hindustan Steel Ltd, Ranchi
DR B. R. DEORAS	Ministry of Railways
SHRI K. C. SOM (<i>Alternate</i>)	
DIRECTOR (M & C) RDSO, LUCKNOW	
PRODUCTION ENGINEER EASTERN RAILWAY, JA- MALPUR (<i>Alternate I</i>)	
ASSISTANT DIRECTOR (M. S.), RDSO, LUCKNOW (<i>Alternate II</i>)	
SHRI N. KRISHNASWAMI	Directorate General of Technical Development, New Delhi
SHRI D. P. LAHIRI	Defence Metallurgical Research Laboratory, Ministry of Defence (R & D)
SHRI A. KAILASAM (<i>Alternate</i>)	
SHRI S. K. LAHIRI	Directorate General of Supplies & Disposals (Inspection Wing) Ministry of Works, Housing & Supply)
SHRI P. G. V. RAO (<i>Alternate</i>)	
SHRI K. P. K. MENON	Ministry of Defence (DGI)
SHRI AMIL MITRA	Indian Institute of Foundrymen, Calcutta
SHRI K. SRINIVASAN (<i>Alternate</i>)	
SHRI P. MITRA	Indian Tube Co Ltd, Jamshedpur
SHRI S. N. MUKERJEE	National Test House, Calcutta
SHRI B. K. MURTHY	Indian Aluminium Co Ltd, Calcutta
SHRI N. GOPALKRISHNAN (<i>Alternate</i>)	
DR S. R. PRAMANIK	Ministry of Steel, Mines & Metals
SHRI K. N. P. RAO	The Tata Iron & Steel Co Ltd, Jamshedpur
SHRI K. P. ROY CHOWDHURY	Indian Non-Ferrous Metals Manufacturers' Association, Calcutta
SHRI R. K. SRIVASTAVA, Deputy Director (Struc & Met)	Director General, ISI (<i>Ex-officio Member</i>)
<i>Secretary</i>	
SHRI SANT SINGH	
Senior Technical Assistant (Struc & Met), ISI	

(Continued on page 2)

INDIAN STANDARDS INSTITUTION
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

(Continued from page 1)

Panel for Code for Designation of Ferrous Castings, SMDC 1:P11

Convener

DEPUTY DIRECTOR (MET-2) Ministry of Railways
RDSO, CHITTARANJAN

Representing

Members

SHRI S. K. DAM
REPRESENTATIVE
REPRESENTATIVE
SHRI N. K. SHUKLA

Burn & Co Ltd, Howrah
The Britannia Engineering Co Ltd, Titaghur
Indian Iron & Steel Ltd, Kulti
Hindustan Motors Ltd, District Hooghly

Indian Standard

CODE FOR DESIGNATION OF FERROUS CASTINGS

0. FOREWORD

0.1 This Indian Standard was adopted by the Indian Standards Institution on 8 October 1968, after the draft finalized by the Metal Standards Sectional Committee had been approved by the Structural and Metals Division Council.

0.2 A code for designation of ferrous castings will be an important step towards identification, uniform marking of products and drawings. Such a standard designation would greatly help the manufacturers and the users of the products concerned.

0.3 This standard has been co-ordinated with the following codes for designation, so that certain measure of uniformity is achieved in the designations:

*IS: 1762-1961 Code for designation of steel

*IS: 2084-1962 Code for designation of pig iron

IS: 2085-1962 Code for designation of ferro-alloys

1. SCOPE

1.1 This standard lays down the principles for code designation of ferrous castings.

2. GENERAL

2.1 Ferrous castings shall be designated by a group of symbols indicating the important characteristics in the following order:

a) Type of castings, and

b) Mechanical properties or chemical composition.

3. SYMBOLS FOR TYPE OF CASTINGS

3.1 Various castings shall have code designations as given below:

<i>Ferrous Castings</i>	<i>Designation</i>
a) Grey iron	FG
b) Malleable iron	
1) Black-heart	BM
2) Pearlitic	PM
3) White-heart	WM
c) Spheroidal or nodular graphite iron	SG
d) Austenitic flake graphite iron	AFG
e) Austenitic spheroidal or nodular graphite iron	ASG
f) Abrasion resistant iron	ABR
g) Steel castings	CS
h) Heat-resistant steel castings	CSH
j) Corrosion-resistant steel castings	CSC

4. SYMBOL FOR MECHANICAL PROPERTIES

4.1 The tensile strength in kgf/mm^2 to follow the group symbol shall be the minimum for the 30-mm section in case of grey iron castings and the minimum for the heaviest section in case of various other castings. Where the minimum tensile strength requirement does not vary with the sectional thickness within the same grade, the group symbol shall be followed by the minimum tensile strength indicated for the grade. In the case of spheroidal or nodular graphite iron castings, the tensile strength shall be followed by the minimum elongation on gauge length $5.65\sqrt{S_0}$.

5. SYMBOL FOR CHEMICAL COMPOSITION

5.1 In the case of grey iron castings where chemical composition is more important than the tensile properties and for alloy iron and alloy steel castings, the group symbol shall be followed by the chemical symbol in accordance with IS: 1762-1961*.

*Code for designation of steel. (Since revised).

6. EXAMPLES

6.1 In order to illustrate, examples of code designations in accordance with this standard are given below:

a) Grey Iron Castings

1) General Engineering Castings

SECTIONAL THICKNESS OF CASTINGS mm	DIAMETER OF TEST BAR AS CAST mm	TENSILE STRENGTH kgf/mm ² Min	DESIGNATION
4 up to 8	13	19	FG 15
Over 8 up to 15	20	17	
Over 15 up to 30	30	15	
Over 30 up to 50	45	13	
15 up to 30	30	40	FG 40
Over 30 up to 50	45	37	

2) Special Grey Iron Castings Where Chemical Composition is More Important, Such as Ingot Mould Castings

CHEMICAL COMPOSITION		DESIGNATION
Element	Percent	FG 35 Si 15
Carbon equivalent (C + 0.3 Si + P)	4.0 to 5.1	
Total carbon, Min	3.5	
Silicon	1.20 to 1.80	
Manganese	0.60 to 0.90	
Chromium, Max	0.15	
Copper, Max	0.10	
Sulphur, Max	0.080	
Phosphorus, Max	0.400	

b) Malleable Iron Castings

1) Black-Heart Malleable Iron Castings

SECTIONAL THICK- NESS OF CASTINGS mm	DIAMETER OF TEST BAR AS CAST mm	TENSILE STRENGTH kgf/mm ² Min	DESIGNATION
All sizes	15	35	BM 35
All sizes	15	32	BM 32
All sizes	15	30	BM 30

2) *Pearlitic Malleable Iron Castings*

SECTIONAL THICKNESS OF CASTINGS mm	DIAMETER OF TEST BAR AS CAST mm	TENSILE STRENGTH kgf/mm ² Min	DESIGNATION
All sizes	15	70	PM 70
All sizes	15	65	PM 65
All sizes	15	55	PM 55
All sizes	15	50	PM 50
All sizes	15	45	PM 45

3) *White-Heart Malleable Iron Castings*

SECTIONAL THICKNESS OF CASTINGS mm	DIAMETER OF TEST BAR AS CAST mm	TENSILE STRENGTH kgf/mm ² Min	DESIGNATION
8 and under	9	36	WM 42
Over 8 up to 13	12	40	
Over 13	15	42	
8 and under	9	28	WM 35
Over 8 up to 13	12	32	
Over 13	15	35	

c) *Spheroidal or Nodular Graphite Iron Castings*

TENSILE STRENGTH kgf/mm ² Min	ELONGATION, PERCENT Min	DESIGNATION
--	----------------------------	-------------

on Gauge Length $l_0 = 5d$

80	2	SG 80/2
70	2	SG 70/2
60	2	SG 60/2
50	7	SG 50/7
42	12	SG 42/12
38	17	SG 38/17

d) Austenitic Flake Graphite Iron Castings

CHEMICAL COMPOSITION		DESIGNATION
<i>Element</i>	<i>Percent</i>	
Carbon, <i>Max</i>	3.00	AFG Ni 16 Cu 7 Cr 2
Silicon	1.00 to 2.80	
Manganese	1.00 to 1.50	
Nickel	13.5 to 17.5	
Copper	5.50 to 7.50	
Chromium	1.00 to 2.50	

e) Austenitic Spheroidal or Nodular Graphite Iron Castings

CHEMICAL COMPOSITION		DESIGNATION
<i>Element</i>	<i>Percent</i>	
Carbon, <i>Max</i>	3.00	ASG Ni 20 Cr 2
Silicon	1.00 to 2.80	
Manganese	0.70 to 1.50	
Nickel	18.0 to 22.0	
Chromium	1.00 to 2.50	
Phosphorus, <i>Max</i>	0.080	

f) Abrasion-Resistant Iron Castings

CHEMICAL COMPOSITION		DESIGNATION
<i>Element</i>	<i>Percent</i>	
Total carbon	3.0 to 3.6	ABR 33 Ni 4 Cr 2
Graphite carbon, <i>Max</i>	0.10	
Silicon	0.3 to 0.8	
Manganese	0.3 to 0.8	
Nickel	3.3 to 5.0	
Chromium	1.4 to 2.5	
Molybdenum, <i>Max</i>	0.75	
Sulphur, <i>Max</i>	0.15	
Phosphorus, <i>Max</i>	0.30	

g) Steel Castings**1) Unalloyed (General Engineering) Steel Castings**

TENSILE STRENGTH	DESIGNATION
kgf/mm ²	
Min	
125	CS 125
105	CS 105

85
71
55
47
41

CS 85
CS 71
CS 55
CS 47
CS 41

2) *Unalloyed Special (High Magnetic Permeability) Castings*

TENSILE STRENGTH

kgf/mm²

35 to 44

41 to 50

DESIGNATION

CSM 35

CSM 41

3) *Alloy Steel Castings*

CHEMICAL COMPOSITION

DESIGNATION

<i>Element</i>	<i>Percent</i>
Carbon	0.45 to 0.55
Silicon	0.10 to 0.35
Manganese	0.50 to 0.80
Chromium	0.90 to 1.20
Vanadium, <i>Min</i>	0.15

CS 50 Cr 1 V 20

h) *Heat-Resistant Steel Castings*

CHEMICAL COMPOSITION

DESIGNATION

<i>Element</i>	<i>Percent</i>
Carbon	1.20 to 1.40
Silicon, <i>Max</i>	2.00
Manganese, <i>Max</i>	1.00
Chromium	26.0 to 30.0
Nickel	4.0 to 7.0
Sulphur, <i>Max</i>	0.050
Phosphorus, <i>Max</i>	0.050

CSH 130 Ni 6 Cr 28

j) *Corrosion-Resistant Steel Castings*

CHEMICAL COMPOSITION

DESIGNATION

<i>Element</i>	<i>Percent</i>
Carbon	0.12 to 0.20
Silicon, <i>Max</i>	1.00
Manganese, <i>Max</i>	1.00
Nickel, <i>Max</i>	1.00
Chromium	11.5 to 14.0
Molybdenum, <i>Max</i>	0.50

CSC 16 Cr 13

INTERNATIONAL SYSTEM OF UNITS (SI UNITS)

Base Units

Quantity	Unit	Symbol
Length	metre	m
Mass	kilogram	kg
Time	second	s
Electric current	ampere	A
Thermodynamic temperature	kelvin	K
Luminous intensity	candela	cd
Amount of substance	mole	mol

Supplementary Units

Quantity	Unit	Symbol
Plane angle	radian	rad
Solid angle	steradian	sr

Derived Units

Quantity	Unit	Symbol	Conversion
Force	newton	N	1 N = 1 kg·1 m/s ²
Energy	joule	J	1 J = 1 N·m
Power	watt	W	1 W = 1 J/s
Flux	weber	Wb	1 Wb = 1 V·s
Flux density	tesla	T	1 T = 1 Wb/m ²
Frequency	hertz	Hz	1 Hz = 1 c/s (s ⁻¹)
Electric conductance	siemens	S	1 S = 1 A/V
Pressure, stress	pascal	Pa	1 Pa = 1 N/m ²

INDIAN STANDARDS INSTITUTION

Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002

Telephones : 26 60 21, 27 01 31

Telegrams : Manaksanstha

Regional Offices:

		Telephone
Western : Novelty Chambers, Grant Road	BOMBAY 400007	37 97 29
Eastern : 5 Chowringhee Approach	CALCUTTA 700072	23-08 02
Southern : C. I. T. Campus, Adyar	MADRAS 600020	41 24 42

Branch Offices:

'Pushpak', Nurmohamed Shaikh Marg, Khanpur	AHMADABAD 380001	2 03 91
'F' Block, Unity Bldg. Narasimharaja Square	BANGALORE 560002	2 76 49
Gangotri Complex, Bhadbhade Road, T.T. Nagar	BHOPAL 462003	6 27 16
2/E Kalpana Area	BHUBANESHWAR 751014	5 36 27
Ahimsa Bldg, SCO 82-83, Sector 17C	CHANDIGARH 160017	2 83 20
5-B-56C L. N. Gupta Marg	HYDERABAD 500001	22 10 83
D-277 Todarmal Marg, Banipark	JAIPUR 302006	6 98 32
117/418 B Sarvodaya Nagar	KANPUR 208005	8 12 72
Patliputra Industrial Estate	PATNA 800013	6 28 08
Hantex Bldg (2nd Floor), Rly Station Road	TRIVANDRUM 695001	32 27